



Acidsafe Adhesive Gel Technical Specifications

Features:

- Tough, flexible adhesive bonds barriers to floor
- Novalac epoxy coating withstands 98% sulfuric acid (spill, splash and fume) and 70% sulfuric acid (continuous immersion)
- No V.O.C.s - 100% solids; allows for minimal disruption of site activities



Acran Item Number	5EAK0002
Impact Resistance	80 inch-pound, ASTM D2794
Tensile Strength	3840 psi, elongation, ASTM D638
Abrasion Resistance	< 0.08g, 1k cycles, CS-17 wheel, 1kg, ASTM D4060
Flexural Strength	7470 psi, 2.9×10^4 psi, modulus, ASTM D790
Hardness	71 shore D, ASTM D2240
Bond Strength	>1000 psi, 100% concrete failure, steel, concrete, ASTM D4541
Pot Life	20 minutes for 18 fluid ounces at 70° F
Linear Coverage (in.)	150
Color	ANSI/ASA 61 gray
Weight (lbs.)	2

Manufacturing Facility:
105 Snyder Road
South Plainfield, NJ 07080

ACRAN SPILL CONTAINMENT

Corporate Headquarters:
599 Albany Ave.
No. Amityville, NY. 11701

T 877- 227- 2615 F 908-769-6991 Email sales@acran.com